

莘茂複合材料股份有限公司 EPOTECH COMPOSITE CORPORATION TEL:886-4-24630896 FAX:886-4-24630806

Email <u>e-service@epotechcorp.com</u>

EPO-RTTM 60 Resin

EPO-RT^{*TM*} series are wet layup and resin transfer moulding epoxy systems that are designed for structural production applications. Several hardeners are available for use with EPO-RT^{*TM*} series. These systems give excellent wet-out of fiberglass, carbon and aramid fibres. EPO-RT^{*TM*} series will cure completely at room temperature, or can be given an elevated temperature cure. The best ratio on EPO-RT^{*TM*} 60 is 100:50 by weight and has an about 100-minute pot life.

Important

This information is furnished without warranty, expressed or implied, except that it is accurate to the best knowledge of Epotech Composite Corporation. The data on this sheet is related only to the specific material designated herein. Epotech Composite Corporation assumes no legal responsibility for the use or reliance upon these data.

